



PRODUCT DATA SHEET

Gillfab® 4522

DESCRIPTION

Gillfab® 4522 is a low smoke sandwich floor panel made from woven fiberglass reinforced phenolic facings bonded to Gillcore® HD meta-aramid honeycomb core.

APPLICATIONS

Flooring panels for containerize cargo holds in all Airbus Industrie 300 series aircrafts

FEATURES

- High impact strength
- Corrosion resistant
- Light weight
- Low smoke generation
- Good burn through resistance
- Service temperature: 180°F (82°C)

AVAILABILITY

Thickness, inch (mm)	0.374 (9.5)
Length and Width, inch (mm)	Maximum 60 x 144 (1,524 x 3,658)
Facing thickness, face/back, inch (mm)	0.020/0.015 (0.508/0.381)

CONSTRUCTION

- Adhesive:** Epoxy
Core: Meta-aramid
Facings Reinforcement: Fiberglass woven cloth
Facings Resin System: Phenolic

SPECIFICATIONS

- AI Technical Specification No. 5360 M1M 000500, Issue 5 (CCC1)
- FAR 25.853 - fire resistant
- ABD 0031 - Smoke density, toxicity, flammability, and burn through

HEALTH PRECAUTIONS

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. A SDS is available at <https://www.thegillcorp.com/msds.php>.

For industrial use only. Keep away from children. Additional information can be found at: www.thegillcorp.com. For sales and ordering information call 1-626-443-6094.





PERFORMANCE PROPERTIES, TYPICAL

TGC Part Number	4522-374
Weight, psf (kg/m ²)	0.609 (2.97)
Long Beam Bending, lb (N)	323 (1,439)
Deflection @ 100 lbs, inch (@445N, mm)	0.83 (21)
Panel Shear, lbs (N)	755 (3,449)
Drum Peel, in-lbs/3" width (N/76mm width)	71 (317)
Stabilize Compression, psi (N/mm ²)	1,690 (11.65)
Impact Strength, ft-lbs (Nm)	4.88 (6.61)
Insert Shear, lbs (N)	2,293 (10,200)
Warpage, in/ft (mm/m)	0 (0)
Flammability	Meets requirements of FAR 25.853 & 855 Appendix F Part I and III

Figures shown reflect typical values and should not be used as design specifications.

Updated: 12/01/19

All recommendations, statements, values and technical data herein are based on tests The Gill Corporation believes to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. Users shall rely on their own information and tests to determine suitability of the product for the intended use and assume all risks and liability resulting from their use of the product. The Gill Corporation's sole responsibility shall be to replace that portion of the product that proves to be defective. The Gill Corporation will not be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements not contained in a written agreement signed by an officer of The Gill Corporation shall not be binding upon The Gill Corporation. Gillfab® and Gillcore® are registered trademarks of The Gill Corporation.